

PAVISTONE EPOXY UV

Non yellowing epoxy binder

RAYSTON
products



DESCRIPTION AND APPLICATIONS

2-component, clear epoxy resin, suitable for use as an aggregate binder. Designed for use as a binder for pavement applications that gives draining floors, with no yellowing over time.

PROPERTIES

Easy to mix and apply, with excellent support and stone wetting ability. Suitable for small repairs or smoothing finishes, mixed with fine grain size sand.

TECHNICAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION				
	Component A		Component B	
Chemical description	Epoxy resin		Polyamine mixture	
Physical state	Liquid		Liquid	
Packaging	Metal container		Metal container	
	10 kg		5 kg	
	3.33 kg		1.66 kg	
Non-volatile content	98%		98%	
Flash point	>120°C		>100°C	
Colour	Colourless		Slightly yellow	
Density	Tempera	Density	Tempera	Density
	ture (°C)	(g/cm³)	ture (°C)	(g/cm³)
	23	1.12	23	1.10
Viscosity	Tempera	Viscosity	Tempera	Viscosity
	ture (°C)	(mPa.s)	ture (°C)	(mPa.s)
	25	100-200	25	7600
VOC	Almost 0		Almost 0	
A/B mixing ratio	A=100, B=54.4 by weight			
	A=89, B=49 by volume			
Mixture properties	Density: 1,1 g/cm³ at 23°C			
	Viscosity: 530 mPa.s at 23°C			
	Colour: slightly yellow			
Pot life	Temperature (°C)		Pot life(100g,min)	
	20		40	
Storage	Keep between 10°C and 30°C, in a dry place			
Use before	12 months after manufacturing date.			

INFORMATION ON THE FINAL PRODUCT	
Final state	Solid film
Colour	Colourless, slightly yellow
Solid density	1,00 g/cm ³
Hardness (shore)	85D
Mechanical properties	Elongation at break: <5% (EN-ISO 527-3)
UV resistance	No noticeable yellowing upon sunlight exposure is to be expected

CHEMICAL RESISTANCE

Surface contact (24 hours, room temperature, 5=ok, 0= not recommended)

Chemical	Result
White spirit	5
Coffee	5
Isopropyl alcohol	5
Methoxypropyl acetate	5
Gasoline	5
Xylene	5
Sodium hydroxide	5
Ethanol	4
Bleach	5
Trichloroisocyanuric acid	5
Formaline	5

Lubricant oil	5
Hydrogen peroxide	4
Acetic acid (10%)	2
Sulphuric acid (30%)	1
Skydrol	5
Ammonia (3%)	5
Diesel	5

SUPPORT REQUIREMENTS

To achieve a good degree of penetration and bonding, support must be:

- 1.Flat and levelled (product is self-levelling).
2. Compact and cohesive (pull off test must show a minimum resistance of 1,4 N/mm²).
3. Even and regular surface.
4. Free from cracks and fissures. If any, they must be previously repaired.
5. Clean and dry, free of dust, loose particles, oils, organic residues or laitance.

TEMPERATURE AND AMBIENTAL CONDITIONS

Optimal temperature range for application is 10°C- 30°C.

These temperatures must be constant throughout drying process.

Application should be done with plenty of air/ventilation.

SUPPORT PREPARATION

Concrete surfaces must be previously prepared by sandblasting or any other suitable means. Remove all dust and loose material before priming.

Cut suitable joints along the concrete slab, depending on the total surface to be covered.

MIXING

Stir and homogenise thoroughly component A and B using a low-speed stirrer. The mixture turns to a homogenous clear liquid. Do not mix more material than the amount usable within the pot life window.

APPLICATION

To ensure good aggregate binding, the resin amount will depend on several points:

- Grain size
- Dust content in the mineral aggregates
- Degree of absorption of the mineral aggregates.

Depending on these points, the required amount of resin will range from 3% to 10% of the mineral aggregates, by weight.

Apply using a suitable spreader. It is advisable to apply a final sealing topcoat made with the same (diluted) resin or Colodur. It is important to prevent excess of sealing product since it will be readily absorbed and will give foamed and discoloured spots.

CURING TIME

For a 500 g/m² thick application.

Conditions	Dry to touch (h)
35°C, 25% rh	2
23°C, 50% rh	8
23°C, 5% rh	9
7°C, 60% rh	>20
-15°C	uncured



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890 - l'Hospitalet de l'Infant - Spain

Tel: +34 977 822 245 - Fax: +34 977 823 977

www.kryptonchemical.com - rayston@kryptonchemical.com

Latest update:

Page:

09/05/2025

1/2

PAVISTONE EPOXY UV



Non yellowing epoxy binder

TOOL CLEANING

Cleaning of tools contaminated with both components must be done with Solvent Rayston.

SAFETY

Pavistone Epoxy UV contains isocyanates. Always follow the instructions provided in the material safety data sheet and take the precaution described there. As a rule, suitable ventilation must be ensured, and any skin contact avoided. This product is intended to be used only for the uses and in the way here described. This product is to be used only by industrial or professional users. It is not suitable for DIY-type uses.

ENVIRONMENTAL PRECAUTIONS

Empty containers must be handled taking the same precautions as if they were full. Containers must be considered as hazardous waste, to be transferred to an authorized waste manager. If there is some residual product in the containers, component A and B can be mixed, always according to the A/B ratio, and allowed to cure. Do not mix volumes bigger than 5 litres to prevent dangerous reactions.

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products and strongly advise to conduct tests "on-site" to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This data sheet supersedes previous versions.



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890 - l'Hospitalet de l'Infant - Spain
Tel: +34 977 822 245 - Fax: +34 977 823 977
www.kryptonchemical.com – rayston@kryptonchemical.com

Latest update:
Page:

09/05/2025
2/2